



Roofing

Summary Application Table—June 2018

Table of Contents

Tap or click a system name to jump to that system's Summary Application Table.

System

Notes

Permathane Aliphatic II

Aliphatic urethane topcoat system for use over 2.7–3.2 pound density polyurethane roofing foam.

Elastacryl FR

Acrylic system for use over 2.7–3.2 pound density polyurethane roofing foam.

Silicone FR

Silicone system for use over 2.7–3.2 pound density polyurethane roofing foam.

Elasta-Gard C Aliphatic

Aliphatic urethane topcoat system for use over concrete surfaces.

Elasta-Gard M Aliphatic

Aliphatic urethane topcoat system for use over metal surfaces.

Elasta-Gard SP Aliphatic

Aliphatic urethane topcoat system for use over single ply membranes such as TPO, PVC, EPDM, etc.

Elasta-Gard BUR/MB Aliphatic

Aliphatic urethane topcoat system for use over smooth surfaced BUR/MB or granulated cap sheet.

Elastacryl M

Acrylic system for use over metal surfaces.

Elastacryl SP

Acrylic system for use over single ply membranes such as TPO, PVC, EPDM, and others.

Elastacryl BUR/MB

Acrylic system for use over smooth surfaced BUR/MB or granulated cap sheet.

Metal Roof Coating

Acrylic urethane system (57010 ACRYLITHANE™ HS2) for use over metal surfaces.

To return to the Table of Contents, tap or click the return icon located at the bottom right of each page.



Permathane Aliphatic II

Coat	Product	Color	Coverage Rate	Mils	Approx Recoat Time @ 75°F
Base	70620-CA	Dark Gray	66 sf/gal	24 WFT/ 18 DFT/	8–12 hrs or tack-free
Topcoat	7490-CA	White	66 sf/gal	24 WFT/ 18 DFT	8–12 hrs or tack-free
Optional Granule Coat	7490-CA <i>#11 Granules</i>	White	100 sf/gal <i>30 lbs/100 sf</i>	16 WFT/ 12 DFT	NA



Elastacryl FR

Coat	Product	Color	Coverage Rate	Mils	Approx Recoat Time @ 75°F
First	7251 or 7261	White	66 sf/gal	24 WFT/ 12 DFT	2–4 hrs or tack-free
Second	7251 or 7261	White	66 sf/gal	24 WFT/ 12 DFT	2–4 hrs or tack-free
Third	7251 or 7261	White	66 sf/gal	24 WFT/ 12 DFT	2–4 hrs or tack-free
Optional Granule Coat	7251 or 7261 <i>#11 Granules</i>	White	80 sf/gal <i>30 lbs/100 sf</i>	20 WFT/ 10 DFT	NA



Silicone FR

Coat	Product	Color	Coverage Rate	Mils	Approx Recoat Time @ 75°F
First Coat	7860 Series	Dark Gray, Gray, White, Tan	62 sf/gal	25 WFT/ 16 DFT	2–4 hrs or tack-free
Second Coat	7860 Series	Dark Gray, Gray, White, Tan	62 sf/gal	25 WFT/ 16 DFT	2–4 hrs or tack-free
Optional Granule Coat	7860 Series <i>#11 Granules</i>	Dark Gray, Gray, White, Tan	80 sf/gal <i>30 lbs/100 sf</i>	20 WFT/ 12 DFT	NA



Elasta-Gard C Aliphatic

Coat	Product	Color	Coverage Rate	Mils	Approx Recoat Time @ 75°F
Primer	7797/7798	NA	300 sf/gal	NA	1.5 hrs
Base	70620-CA	Dark Gray	66 sf/gal	24 WFT/ 18 DFT	8-12 hrs or tack-free
Topcoat	7490-CA	White	66 sf/gal	24 WFT/ 18 DFT	8-12 hrs or tack-free
Optional Granule Coat	7490-CA <i>#11 Granules</i>	White	100 sf/gal <i>30 lbs/100 sf</i>	16 WFT/ 12 DFT	NA



Elasta-Gard M Aliphatic

Coat	Product	Color	Coverage Rate	Mils	Approx Recoat Time @ 75°F
Primer	7797/7798	NA	400 sf/gal	NA	1.5 hrs
Base	70630	White, Tan, Gray	133 sf/gal	12 WFT/ 9 DFT	6 hrs or tack-free
Topcoat	7490-CA	White	133 sf/gal	12 WFT/ 9 DFT	6 hrs or tack-free
Optional Granule Coat	7490-CA <i>#11 Granules</i>	White	100 sf/gal <i>30 lbs/100 sf</i>	16 WFT/ 12 DFT	NA



Elasta-Gard SP Aliphatic

Coat	Product	Color	Coverage Rate	Mils	Approx Recoat Time @ 75°F
Primer	Contact NEOGARD®	NA	Varies	NA	Varies
Base	70620-CA	Dark Gray	66 sf/gal	24 WFT/ 18 DFT	8–12 hrs or tack-free
Topcoat	7490-CA	White	66 sf/gal	24 WFT/ 18 DFT	8–12 hrs or tack-free
Optional Granule Coat	7490-CA <i>#11 Granules</i>	White	100 sf/gal <i>30 lbs/100 sf</i>	16 WFT/ 12 DFT	NA

Note: Refer to the NEOGARD® Fluid-Applied Roof Coating Systems Manual for seam detail options.



Elasta-Gard BUR/MB Aliphatic

Coat	Product	Color	Coverage Rate	Mils	Approx Recoat Time @ 75°F
Primer	7780/7781	NA	300 sf/gal	NA	1.5 hrs
Base	70620-CA	Dark Gray	40 sf/gal	40 WFT/ 30 DFT	8–12 hrs or tack-free
Topcoat	7490-CA	White	66 sf/gal	24 WFT/ 18 DFT	8–12 hrs or tack-free
Optional Granule Coat	7490-CA <i>#11 Granules</i>	White	100 sf/gal <i>30 lbs/100 sf</i>	16 WFT/ 12 DFT	NA

Note: Refer to the NEOGARD® Fluid-Applied Roof Coating Systems Manual for seam detail options.



Elastacryl M

Coat	Product	Color	Coverage Rate	Mils	Approx Recoat Time @ 75°F
Primer	7797/7798	NA	400 sf/gal	NA	6 hrs or tack-free
First	7251 or 7261	White	66 sf/gal	24 WFT/ 13 DFT	2–4 hrs or tack-free
Second	7251 or 7261	White	66 sf/gal	24 WFT/ 13 DFT	2–4 hrs or tack-free
Optional Granule Coat	7251 or 7261 <i>#11 Granules</i>	White	80 sf/gal <i>30 lbs/100 sf</i>	20 WFT/ 10 DFT	NA



Elastacryl SP

Coat	Product	Color	Coverage Rate	Mils	Approx Recoat Time @ 75°F
Optional Primer	Contact NEOGARD®	NA	Varies	NA	Varies
First	7251 or 7261	White	66 sf/gal	24 WFT/ 13 DFT	2–4 hrs or tack-free
Second	7251 or 7261	White	66 sf/gal	24 WFT/ 13 DFT	2–4 hrs or tack-free
Optional Granule Coat	7251 or 7261 #11 Granules	White	80 sf/gal 30 lbs/100 sf	20 WFT/ 10 DFT	NA

Note: Refer to the NEOGARD® Fluid-Applied Roof Coating Systems Manual for seam detail options.



Elastacryl BUR/MB

Coat	Product	Color	Coverage Rate	Mils	Approx Recoat Time @ 75°F
Optional Primer	7780/7781	NA	300 sf/gal	NA	6 hrs or tack-free
First	7251 or 7261	White	66 sf/gal	24 WFT/ 13 DFT	2–4 hrs or tack-free
Second	7251 or 7261	White	66 sf/gal	24 WFT/ 13 DFT	2–4 hrs or tack-free
Optional Granule Coat	7251 or 7261 <i>#11 Granules</i>	White	80 sf/gal <i>30 lbs/100 sf</i>	20 WFT/ 10 DFT	NA

Note: Refer to the NEOGARD® Fluid-Applied Roof Coating Systems Manual for seam detail options.



Metal Roof Coating

Coat	Product	Color	Coverage Rate	Mils	Approx Recoat Time, 75°F/23°C
Primer	15050 Ureprime [®] HS4	White	200–300	4.5–8 WFT 5–8 DFT	4 hrs or tack-free
Topcoat	57010 Acrylithane [™] HS2	Various	250–330	4.5–6.25 WFT 3–4 DFT	4 hrs or tack-free
Optional Clear Coat	57010 Acrylithane [™] HS2	Various	250–330	4.5–6.25 WFT 3–4 DFT	NA





NEOGARD[®]
CONSTRUCTION COATINGS
A part of the Hempel Group

NEOGARD[®], a Division of Hempel (USA), Inc.

2728 Empire Central - Dallas, Texas 75235 - Phone (214) 353-1600 - Fax (214) 357-7532 - www.neogard.com