

Product Data Sheet

FC7500/FC7960 — Fast-Cure Polyurethane Base Coat 45063: Base 45067 : Curing Agent 95077



Description: FC7500/FC7960 (Hempel 45067/95077) is a two-component, fast-cure polyurethane base coat.

Recommended use: As a waterproofing membrane for pedestrian and vehicular traffic bearing surfaces, where fast turnaround time and/or solvent free materials are required. Suitable areas include parking garages, stadiums, balconies, plaza decks, walkways, rooftop recreation areas, and mechanical rooms.

Features: Meets South Coast Air Quality Management District (SCAQMD) VOC requirements.

Certificates/approvals: LEED: MRc5, IEQc4.2, BDc4, IDc4
UL: TGFU.R6034
Miami-Dade: NOA No.: 14-0902.10
City of Los Angeles: RR# 25702

Availability: Available in North America. Not included in Group Assortment; other regions must confirm.

Colors and packaging:

FC7500 (4506716650)	Gray	5- and 1- gallon
FC7960 (9507700000)	NA	1-pint, 1-gallon

Physical constants:

Tensile strength	1,500 psi	ASTM D412
Elongation	500%	ASTM D412
Permanent set	<20%	ASTM D412
Tear resistance	150 pli	ASTM D1004
Water resistance	1% at 7 days	ASTM D471
MVT at 20 mils	5 English Perm	ASTM E96
Shore A	74–79	ASTM D2240
Adhesion to: 70714/70715 7760/7761 7780/7781 Inter-Coat	400 psi	ASTM D4541
Weight/gallon (mixed)	9.7 lbs/gal	ASTM D1475
Weight solids (mixed)	99%	ASTM C1250
Volume solids (mixed)	99%	Calculated
VOC (mixed)	<5 g/L	EPA Method 24
Viscosity (mixed)	2,000 cps	ASTM D2196
Flash point	>250°F/>121°C	ASTM D3278
Shelf life	1 year	
Fire resistance (spread of flame)	Class A (as part of a system)	ASTM E108/UL 790

The above tested results are typical values. Individual lots may vary up to 10% from the typical value. Further technical information can be found at www.neogard.com.

Application details:

Version, mixed product **45063**
Mixing ratio: Base 45067 : Curing Agent 95077
9 : 1 by volume

Mixing instructions: Pre-mix base for 3–5 minutes before adding curing agent. Mix for a minimum of 5 minutes before applying. Jiffy Mixer paddle recommended.

Application method: Roller or squeegee

Thinner (max.vol.): 7055 Odorless Reducer (086JB1L001) (10%)

Pot life: 20–30 minutes at 75°F/23°C

Cleaning of tools: Hempel's Thinner 08080 (xylene)

Product Data Sheet

FC7500/FC7960 — Fast-Cure Polyurethane Base Coat
45063: Base 45067 : Curing Agent 95077



Safety:	Handle with care. Use with adequate ventilation. Before and during use, observe all safety labels on packaging and paint containers, consult Neogard Safety Data Sheets and follow all local or national safety regulations.
Application conditions:	Substrate temperature must be between 40°F/4°C and 110°F/32°C.
Preceding coat:	According to Neogard Guide Specifications.
Subsequent coat:	According to Neogard Guide Specifications.
Storage temperature:	Store in a cool area to ensure full shelf life. Recommended temperature: 75°F/23°C.
Remarks:	Not intended for use as a topcoat. Maximum time for UV exposure: 5 days. Not recommended for constant immersion. Do not apply over asphaltic compounds. For on-grade applications, substrates constructed over unvented metal decks or between-slab applications, contact Neogard Technical Service.

Note: FC7500/FC7960 is for professional use only.

Issued by: Hempel (USA) – 45063

This Product Data Sheet supersedes those previously issued.

Manufacturer warrants that the physical properties of the product reported above will meet the standards and deviations of the associated ASTM test method. MANUFACTURER HEREBY EXPRESSLY DISCLAIMS ANY AND ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION, ANY IMPLIED WARRANTY OF MERCHANTABILITY AND/OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE. Buyer must make its own determination of the suitability of any product for its use, whether such product is used alone or in combination with other materials. To the extent this or any of Manufacturer's products is proven to be defective, Buyer's sole remedy shall be limited to the replacement of such defective product, exclusive of any costs of labor. MANUFACTURER SHALL NOT BE LIABLE OR OBLIGATED FOR ANY LOSS OR CONSEQUENTIAL OR OTHER DAMAGE INCURRED DIRECTLY OR INDIRECTLY BY BUYER OR ANY OTHER PERSON OR ENTITY THAT ARISES IN ANY WAY IN RELATION TO THIS OR ANY OF MANUFACTURER'S OTHER PRODUCTS. Nothing contained herein shall be construed to constitute inducement or recommendation to practice any invention covered by any patent without authority of the owner of the patent. No Applicator is or should be viewed as an employee or agent of Manufacturer. FC7500-FC7960-PDS ksk 03222021.docx

Neogard®, a part of Hempel
2728 Empire Central - Dallas, Texas 75235 - Phone (214) 353-1600 - Fax (214) 357-7532 - www.neogard.com